


Spectrum Test Report



Colorimetric Parameters

Chromaticity Coordinate: $x=0.3162$ $y=0.3319$ $u'=0.1992$ $v'=0.4704$
 CCT=6297K (Duv=0.0029) Dominant WL:Ld =490.6nm Purity=5.9%
 Peak WL:Lp=449.8nm FWHM=21.8nm
 Render Index:Ra=72.6
 R1 =71 R2 =76 R3 =76 R4 =74 R5 =72 R6 =66 R7 =82
 R8 =63 R9 =0 R10=40 R11=70 R12=40 R13=71 R14=86 R15=68

Photometric & Radiometric Parameters

Flux=4091 lm Eff.:70.17 lm/W Fe=12.89 W
 (EQE):127.31%

Electrical parameters


V=13.20 V I=4.417 A P=58.31 W PF=1.000
 Freq=0.00 Hz

Status: Integral T = 56 ms Ip = 43487 (66%)
 Test Mode: Fast Test; Sensitivity = High; Tecool: ON

Model:W3560ALS
 Test By:胡军
 Temperature:23 °C
 Manufacturer:

Number:1#
 Date:2025-07-18
 Humidity:60%
 Remarks:

Spectrum Test Report



Colorimetric Parameters

Chromaticity Coordinate: $x=0.3166$ $y=0.3355$ $u'=0.1981$ $v'=0.4723$
 CCT=6260K (Duv=0.0046) Dominant WL:Ld =493.4nm Purity=5.5%
 Peak WL:Lp=451.6nm FWHM=23.6nm
 Render Index:Ra=74.0
 R1 =71 R2 =78 R3 =80 R4 =74 R5 =72 R6 =69 R7 =85
 R8 =63 R9 =0 R10=45 R11=69 R12=41 R13=73 R14=89 R15=68

Photometric & Radiometric Parameters

Flux=2367 lm Eff.:81.71 lm/W Fe=7.455 W
 (EQE):148.53%

Electrical parameters

V=13.20 V I=2.195 A P=28.97 W PF=1.000
 Freq=0.00 Hz

Status: Integral T = 113 ms Ip = 48722 (74%)
 Test Mode: Fast Test; Sensitivity = High; Tecool: ON

Model:W3560ALS 稳定
 Test By:胡军
 Temperature:23 °C
 Manufacturer:

Number:1#
 Date:2025-07-18
 Humidity:60%
 Remarks: